

## PROPERTIES OF

## **GRAPHITE GRADE ELLOR+18**

## GENERAL PROPERTIES

Isomolded, very fine grain, high		Typical Values	
strength. high density, isotropic		<b>English Units</b>	SI Units
graphite. Maximum inert service			
temperature 5,000 F (2760 ℃).	Bulk Density	111 lbs/ft <sup>3</sup>	1,78 g/cm <sup>3</sup>
Standard Sizes: 308 x 620 x 1830 mm	Grain Size	0.0005 inch	12 µm
308 X 620 x 915 mm	Specific Resistance	0.00054 ohm-in	1370 µohm.cm
	Flexural Strength	6,500 psi	45 MPa
	Tensile Strength	4,200 psi	29 MPa
	Compressive Strength	14,300 psi	99 MPa
	Hardness (Shore)	55	55
	Hardness (Rockwell L)	98	98
TYPICAL	Coefficient of Thermal	2.9 x 10E-6/°F	5,2 x 10E-6/°C
APPLICATIONS	Expansion (400 to 500°C)		
Formulated for EDM applications requiring medium surface finish and high metal removal rates.	Porosity	12%	12%
Surface finish 4.5 to 9 Raµm.	Thermal Conductivity	55 Btu-Ft/Ft <sup>2</sup> Hr <sup>o</sup> F	95 W/m°C
	Ash	400 ppm	400 ppm

13-May-2010 Rev 01

The specification or data herein contained are only given for indication, without any undertakings whatsoever. Their publication does not suggest the matter is free of any rights whatsoever. Furthermore, due to constant evolution of techniques and norms, we reserve the right to modify, at any time, the characteristics and specifications contained in this document. MERSEN refuses all and any responsibility concerning their use whatever the purpose or application. Any copy, reproduction or information herein contained, in whole or in part, made without MERSEN written consent, is forbidden according to the laws of France and particularly the law nr. 92-597 of July 1st 1992 relating to the copyright.

In North America contact:
Mersen USA St Marys-PA Corp.

215 Stackpole Street Saint Marys, PA 15857 USA Tel: (814) 781 - 1234

Fax: (814) 781 - 8570

In Europe contact:

**Mersen France Gennevilliers S.A.S** 

BP 148 - 41, rue Jean - Jaurès F - 92231 Gennevilliers - France

Tel: (33) 1 41 85 43 00 Fax: (33) 1 41 85 43 15